



## COLOR WOOD PUTTY

### AREA OF APPLICATION

In the wood protection system for removing wood defects and damage, such as cracks, dents, scratches in internal spaces and outdoors

### PROPERTIES

- easy to apply
- good sanding

| TECHNICAL DATA             |  |
|----------------------------|--|
| COMPOSITION                | Alkyd binder, pigment, fillers   |
| COLOR SHADES               | White  |
| TINTING                    | /  |
| GLOSS                      | Matt   |
| DENSITY                    | 1,6 g/ml   |
| THINNING                   | Not to be thinned  |
| EU VOC category and limits | IIA(g), 350 g/l (2010); the product contains: max. 340 g/l   |
| PACKAGING UNITS            | 0,5 kg, 0,9 kg   |
| SHELF LIFE                 | The shelf life of an originally sealed and suitably stored product (temperature ranging from +5° C to +35° C, in a dry place) is indicated on the packaging. |

| INSTRUCTIONS FOR USE                      |   |
|---|---|
| APPLICATION METHODS                       | Trowel  |
| WORKING CONDITIONS                        | The paint, air and surface temperature should be at least +5° C.  |
| DRYING<br>(T = +20° C, rel. humidity 65%) | Sanding after 6 hours, the following layer after 24 hours<br>At lower temperatures and higher relative humidity, the drying time is extended. |
| COVERAGE                                  | Depends on the size of damage   |
| CLEANING TOOLS                            | <b>COLOR ENAMEL THINNER</b>   |

### SURFACE PREPARATION

#### 1. Wooden surface

The humidity must not exceed 15% for coniferous trees, and 12% for deciduous trees. The dry surface is to be sanded and cleaned, and any wax, resin or grease should be removed with **COLOR NITRO thinner**.

### COATING SYSTEMS

| SURFACE |         | SURFACE PREPARATION            | IMPREGNATION                            | PUTTYING                | PRIMER                          | TOP COAT               |
|---------|---------|--------------------------------|---|-------------------------|---------------------------------|------------------------|
| WOOD    | indoor  | sanding, removal of impurities | /                                       | <b>COLOR WOOD PUTTY</b> | 1x <b>COLOR PRIMER FOR WOOD</b> | 2x <b>COLOR ENAMEL</b> |
|         | outdoor |                                | 1x <b>COLOR WOODSTAIN</b><br>colourless |                         | 2x <b>COLOR PRIMER FOR WOOD</b> |                        |

### NOTES AND SPECIAL FEATURES

- Strong odor of organic solvents may develop in poorly ventilated spaces. We therefore do not recommend using coatings that are alkyd resin based in the solvent for painting interior furniture.